

FRAGMENT-MNP: A model of micro- and nanoplastic fragmentation in the environment

Sam Harrison ¹, Cansu Uluseker ¹, Patrizia Pfohl ², Katherine Santizo^{2,3}, Joana Sipe ^{4,7}, Brandon Lopez⁴, Antonia Praetorius ⁵, Richard K. Cross ⁶, Gbotemi A. Adediran ^{6,8}, Claus Svendsen ⁶, Wendel Wohlleben ², and Mark Wiesner ⁴

1 UK Centre for Ecology & Hydrology, Library Avenue, Bailrigg, Lancaster, LA1 4AP, United Kingdom 2 BASF SE, Carl-Bosch-Str. 38, 67056 Ludwigshafen, Germany 3 Cefic aisbl, Rue Belliard 40 (box 15) – 1040, Brussels, Belgium 4 Duke University, Durham, NC 27708, United States 5 University of Amsterdam, 1090 GE Amsterdam, Netherlands 6 UK Centre for Ecology & Hydrology, Benson Lane, Crowmarsh Gifford, Wallingford, OX10 8BB, United Kingdom 7 Ira A. Fulton Schools of Engineering, Arizona State University, 1151 S Forest Ave, Tempe, AZ, United States 8 School of Earth and Environment, University of Leeds, Leeds, LS2 9JT, United Kingdom

DOI: 10.21105/joss.08061

Software

- Review C
- Repository 🗗
- Archive ⊿

Editor: Evan Spotte-Smith ♂ ◎ Reviewers:

- @ashahide
- Øjoeweaver

Submitted: 18 February 2025 Published: 12 June 2025

License

Authors of papers retain copyright and release the work under a Creative Commons Attribution 4.0 International License (CC BY 4.0).

Summary

The degradation and fragmentation of plastics in the environment is an important but relatively poorly characterised process. Fragmentation leads to the formation of micro- and nanoplastics, and research has shown that particle size and shape, and thereby fragmentation, impacts a variety of processes, such as the ability of organisms to uptake plastics, and the movement of plastics around the environment (Thompson et al., 2024; Thornton Hampton et al., 2022). In this paper, we present the FRAGMENT-MNP model as an open-source mechanistic model of micro- and nanoplastic degradation and fragmentation. FRAGMENT-MNP predicts how pieces of plastic can break part (fragment), providing invaluable insights into fragmentation dynamics to help develop our understanding of plastic degradation and fragmentation, and offering predictive capabilities to enable better prediction of the fate and exposure of plastics in the environment.

Statement of need

By modifying particle sizes and shapes, fragmentation influences the potential risk caused by plastics in the environment. Therefore, to assess the risk caused by plastic pollution, understanding fragmentation is crucial. Predictive models are essential in helping this assessment, enabling us to fill gaps in observation data, better understand the results of experiments, and predict theoretical scenarios, such as in prospective risk assessments. Despite this, existing models that predict plastic transport, fate and exposure to organisms either do not consider fragmentation, include it only as a loss process (Quik et al., 2023), treat fragmentation as independent of the properties and residence time in the environment (Koelmans et al., 2017), or consider fragmentation as cascading (fragmenting mass can only be partitioned to the next biggest size class, rather than allowing the formation of nano-scale fragments) (Domercq et al., 2022; Kaandorp et al., 2021). In reality, fragmentation depends on the environmental stresses encountered in the environment, such as photolysis by sunlight, hydrolysis by water, enzymatic action and mechanical disruption causing the break-apart of particles (e.g. the action of waves or bioturbation by soil invertebrates). Fragmentation has also been shown to often occur via surface erosion into nanoscale fragments (Meides et al., 2021; Menzel et al., 2022), rather than in a cascading manner. There is a clear need for flexible and accessible model that can



account for these factors, and FRAGMENT-MNP fills this gap.

Overview of the model

The model is fully documented at https://fragmentmnp.ceh.ac.uk. Here, we provide a brief overview of its main conceptualisation and functionality.

Particle concentrations c_k are represented in binned size classes k, with the model allowing for the fragmentation of particles from larger to smaller size classes, and the dissolution of particles into a dissolved size class with concentration c_{diss} . Conceptually, the dissolved fraction consists of oligomers, monomers and volatile organic compounds. The solutions are obtained by numerically solving the following set of differential equations:

$$\begin{split} \frac{dc_k}{dt} &= -k_{\text{frag},k}c_k + \sum_i f_{i,k}k_{\text{frag},i}c_i - k_{\text{diss},k}c_k \\ &\frac{dc_{\text{diss}}}{dt} = \sum_k k_{\text{diss},k}c_k \end{split}$$

Here, $k_{\text{frag},k}$ is the fragmentation rate constant of size class k, $f_{i,k}$ is the fraction of daughter fragments produced from a fragmenting particle of size i that are of size k, and $k_{\text{diss},k}$ is the dissolution rate from size class k. The rate constants k_{frag} and k_{diss} can be a function of time and particle surface area, and thus are represented internally as 2D arrays. The shape of these dependencies can be controlled by model input parameters, which allow for constant, linear, polynomial, power law, exponential, logarithmic or logistic dependencies. This flexible parameterisation allows for rate constants to model a variety of physical phenomena, such as the modulation of fragmentation as polymer particles undergo weathering in the environment.

FRAGMENT-MNP is released as a pip package (pip install fragmentmnp) and comes with example configuration and data, to enable users to get started using the model in as little time as possible. A bare minimum model run is shown below, which uses these examples to run an arbitrary fragmentation scenario (with no dissolution):

```
from fragmentmnp import FragmentMNP
from fragmentmnp.examples import minimal_config, minimal_data
# Create the model and pass it the example config and data
fmnp = FragmentMNP(minimal_config, minimal_data)
# Run the model
output = fmnp.run()
# Plot the results
output.plot()
```





Figure 1: Example model output showing the time evolution of particle size distributions undergoing fragmentation

Related work

The development of FRAGMENT-MNP is part of broader efforts to further our understanding of microplastics in the environment. For example, work is ongoing to integrate various data collated in the project that funded this work. These data include laboratory experiments that subjected a broad selection of polymers to various environmental stresses, including photolysis (Pfohl et al., 2025), hydrolysis and enzymatic activity. In this work, we aim to generate a database of fragmentation and dissolution rates across a range of polymers and stresses, which can be scaled to realistic stress combinations encountered by plastics in different environmental compartments. These data are providing important parameters to broader models of plastics in the environment, such as the UTOPIA unit-world model of microplastic exposure (Domercq et al., 2025). This model was recently used in a United Kingdom government (Department for Environment, Food and Rural Affairs; Defra) report on risk mitigation options against intentionally added microplastics (eftec & UKCEH, 2025). Also ongoing is the development of other models covering emissions, additive release, long-range transport and exposure, as part of associated projects funded by the European Chemical Industry Council Long-Range Research Initiative (Cefic-LRI; projects ECO56-60 and ECO68).

Author contributions

SH, CU and BL developed the code behind FRAGMENT-MNP. All authors contributed to the conceptualisation and functionality of the model. This included, but was not limited to, performing laboratory experiments that provided insights into fragmentation mechanisms, which ultimately informed elements such as input data requirements, time and surface area dependencies of rate constants, and output data and plotting capabilities. SH, MW, WW, AP and CS supervised the model development and broader project.

Acknowledgements

Thank you to Cefic-LRI for providing funding for this work, under project number ECO59.



References

- Domercq, P., Praetorius, A., Harrison, S., & MacLeod, M. (2025). UTOPIA. https://github. com/microplastics-cluster/UTOPIA_model
- Domercq, P., Praetorius, A., & MacLeod, M. (2022). The Full Multi: An open-source framework for modelling the transport and fate of nano- and microplastics in aquatic systems. *Environmental Modelling & Software*, 148, 105291. https://doi.org/10.1016/j. envsoft.2021.105291
- eftec, & UKCEH. (2025). Option Appraisal for Intentionally Added Microplastics (No. CB04121). Defra. https://sciencesearch.defra.gov.uk/ProjectDetails?ProjectId=21802
- Kaandorp, M. L. A., Dijkstra, H. A., & Sebille, E. van. (2021). Modelling size distributions of marine plastics under the influence of continuous cascading fragmentation. *Environmental Research Letters*, 16(5), 054075. https://doi.org/10.1088/1748-9326/abe9ea
- Koelmans, A. A., Kooi, M., Law, K. L., & Sebille, E. van. (2017). All is not lost: Deriving a top-down mass budget of plastic at sea. *Environmental Research Letters*, 12(11), 114028. https://doi.org/10.1088/1748-9326/aa9500
- Meides, N., Menzel, T., Poetzschner, B., Löder, M. G. J., Mansfeld, U., Strohriegl, P., Altstaedt, V., & Senker, J. (2021). Reconstructing the Environmental Degradation of Polystyrene by Accelerated Weathering. *Environmental Science & Technology*, 55(12), 7930–7938. https://doi.org/10.1021/acs.est.0c07718
- Menzel, T., Meides, N., Mauel, A., Mansfeld, U., Kretschmer, W., Kuhn, M., Herzig, E. M., Altstädt, V., Strohriegl, P., Senker, J., & Ruckdäschel, H. (2022). Degradation of low-density polyethylene to nanoplastic particles by accelerated weathering. *Science of The Total Environment*, 826, 154035. https://doi.org/10.1016/j.scitotenv.2022.154035
- Pfohl, P., Santizo, K., Sipe, J., Wiesner, M., Harrison, S., Svendsen, C., & Wohlleben, W. (2025). Environmental degradation and fragmentation of microplastics: Dependence on polymer type, humidity, UV dose and temperature. *Microplastics and Nanoplastics*, 5(1), 7. https://doi.org/10.1186/s43591-025-00118-9
- Quik, J. T. K., Meesters, J. A. J., & Koelmans, A. A. (2023). A multimedia model to estimate the environmental fate of microplastic particles. *Science of The Total Environment*, 882, 163437. https://doi.org/10.1016/j.scitotenv.2023.163437
- Thompson, R. C., Courtene-Jones, W., Boucher, J., Pahl, S., Raubenheimer, K., & Koelmans, A. A. (2024). Twenty years of microplastic pollution research—what have we learned? *Science*, 386(6720), eadl2746. https://doi.org/10.1126/science.adl2746
- Thornton Hampton, L. M., Brander, S. M., Coffin, S., Cole, M., Hermabessiere, L., Koelmans, A. A., & Rochman, C. M. (2022). Characterizing microplastic hazards: Which concentration metrics and particle characteristics are most informative for understanding toxicity in aquatic organisms? *Microplastics and Nanoplastics*, 2(1), 20. https://doi.org/10.1186/s43591-022-00040-4